

AC 96A

HYDRAULICALLY PRESSED MAGNESIA STABILISED ZIRCONIA PARTS

Typical Chemical Analysis

	%
SiO ₂	2.10
TiO ₂	0.15
Fe ₂ O ₃	0.12
Al ₂ O ₃	1.57
CaO	0.20
MgO	3.55
ZrO ₂ + HfO ₂	92.08

Physical Properties

Apparent Porosity (%)	18
Bulk Density (kg/m ³)	4650

Thermal Properties

Specific heat (J/kgK)	550 - 810	(20°C - 2000°C)
Thermal conductivity (W/mK)	0.8 - 1.8	(20°C - 2000°C)
Coefficient of thermal expansion (K ⁻¹)	(6.2 - 9.6) x 10 ⁻⁶	(20°C - 1600°C)

General Properties

Maximum Service Temperature (°C)	2000	
Specific Resistance (Ωcm)	12.8 - 1.0	(1250°C - 2000°C)

The material utilises partially stabilized zirconias to enhance the thermal shock resistance under repeated temperature cycling. Magnesia stabilized zirconia can be used to high temperatures and is the preferred grade when possible reactions with CaO are not tolerable. The figures are typical and do not constitute or imply a specification.

All zirconia fired refractories are manufactured to specifically designed formulae of grain sizes and bonds depending on the application for which they are used.

Forming is carried out in a hydraulic press, ensuring that pressure is applied evenly in all directions, so that the density of the product is consistent throughout.

The above information is, to the best of our knowledge, correct at the time of writing, but is given without guarantee or responsibility since the conditions of use are beyond our control. Magna Industrials Ltd disclaim liability for loss or damage suffered from use of this data and no liability is accepted for use of this product which infringes any patent.